

MTG 145-12

12V-150Ah - GEL Battery

APPLICATIONS



Electric Vehicles (EV)
Home Mobility Equipment (HME)
Cleaning Equipment
Solar Applications
All deep cycle applications

SPECIFICATIONS				
Nominal Voltage			12V	
80% DoD Voltage	Cutoff		11.4V (1,90 VPC)	
Nominal capacity	@20 hour rate	1.75VPC	150Ah	
Capacity at 25°C	Capacity at 25°C	10 hour rate	146Ah	
		5 hour rate	129Ah	
Shelf time @20°C	up to 70%	in months	12	
Self discharge		per month	<3% (20°C)	
Operating temperature for (dis)charge			-10°C to + 50°C	

FEATURES



- Maintenance-free bloc batteries in Gel technology
- Stable high current performance for extreme conditions
- High-class patented safety valve
- Valve-regulated lead-acid battery filled with thixotropic gel
- Classified as a non-spillable battery
- 700 cycles according to IEC 61427 / 60896-21/22



DIMENSI	ONS	
Dimensions LxWxH (T) in mm		512 x 222 x 221 (241)
Weight		50kg (±2%)
Terminal		SAE / A-pole
Terminal torque setting		n.a.
BCI-Group		4D

CHARGING PROFILE (25°C in cyclic application)				
IU Charging	l =	Min 16Amp / max. 23Amp		
	U =	2.43 per cell		
IUI Charging	I ¹ =	Min. 16Amp / max. 23Amp		
	U =	2.38V per cell		
	I ² =	Max. 2Amp (for max. 4 hours to max. 2.65V per cell)		
Float-Voltage	U-float =	2,30VPC		
Temperature compensation is 3 Mv per degree°C up or down from 25°C				


CYCLE LIFE



To maximize the cycle life of the battery, we recommend to charge the battery fully after use. The total life of the battery, is very dependant on the correct charge and depth of discharge per cycle.







GEL Cycle Life vs Depth of Discharge at +25°C Based on IEC 254-1

